

- Operating temperature range  
-75°C to +150°C
- Flame retarded
- System-25 tubing
- Shrink ratio 2:1

## DR-25

Heat-shrinkable, flexible,  
chemical and abrasion resistant  
tubing

Raychem DR-25 heat-shrinkable tubing is flexible and abrasion resistant. One of an extensive range of Raychem heat-shrinkable products, it is made from a radiation cross-linked elastomeric material specially formulated for optimum high temperature fluid resistance, and long term heat resistance. The operating temperature of DR-25

tubing is from -75°C to +150°C for long periods. Shrinking to 50% of its supplied diameter when heated, 10 standard sizes of DR-25 tubing will cover the diameter range from 1.6 mm to 70 mm. The product is printed with the product description and size.

DR-25 tubing is suitable as a jacketing material for military vehicle cables and harnesses. When used in conjunction with System-25 heat-shrinkable moulded shapes and S1125 high performance adhesive, these products provide a complete cable harness system capability.

### Temperature rating

Operating temperature range:	-75°C to +150°C
Minimum full recovery temperature:	+175°C

### Ordering information



Inside diameter		Wall thickness	Standard package		
D (min) Expanded as supplied	d (max) Recovered after heating	W (nom) Recovered after heating	Spool quantity	Weight	Ordering description
mm	mm	mm	m	g/m	
3.2	1.6	0.76	50	7	DR-25-1/8-0
4.8	2.4	0.84	50	12	DR-25-3/16-0
6.4	3.2	0.89	50	15	DR-25-1/4-0
9.5	4.8	1.02	50	25	DR-25-3/8-0
12.7	6.4	1.22	30	39	DR-25-1/2-0
19.0	9.5	1.45	30	68	DR-25-3/4-0
25.4	12.7	1.78	30	111	DR-25-1-0
38.0	19.0	2.41	15	223	DR-25-1 1/2-0
51.0	25.4	2.79	22	341	DR-25-2-0
76.0	38.0	3.18	15	571	DR-25-3-0

The largest size which will recover snugly over the component to be covered should be ordered.

The wall thickness of the tubing will be less than specified if recovery is restricted during shrinkage.

Other lengths and sizes are available subject to special order.

### Standard colours

Colour	Black
Code	0

---

# DR-25

---

## Approvals

---

MIL-DTL-23053/16 except  $1/8$  and  $3/16$   
VG95343 Part 5 Type D  
VDE 0341/Pt 9005  
Def Stan 59-97 Issue 3 Type 6B  
BS 4G-198 Part 3 10A

---

## Performance

---

Test	Test method	Test requirement	
Heat ageing:	ISO188 (168 h at 160°C)	Tensile strength:	8 MPa (min)
		Ultimate elongation:	200% (min)
Flexibility (2% secant):	ASTM D882	50 MPa (max)	
Dielectric strength:	IEC 243	8 MV/m (min)	
Flammability:	ASTM D2671 (Procedure A)	Size $1/2$ :	15 s (max)
Fluid resistance:	24 h at various temperatures ISO37	Tensile strength:	10 MPa (min)
		Ultimate elongation:	300% (min)
		Diesel fuel at 70°C	
		Hydraulic (H515) at 70°C	
		Lubricating oil (0.156) at 100°C	

---

For full product performance details consult Raychem Specification RK 6008/1.

---

## Specifications

---

Raychem Specification RK 6008/1.  
Material Safety Data Sheet available on request.  
Installation instructions available on request.

---

Raychem and DR-25 are trademarks of Raychem Interconnect, a division of Tyco Electronics Corporation.

---

Raychem Interconnect  
Cheney Manor Industrial Estate  
Swindon, Wiltshire SN2 2QE  
Tel: (44)-1793-528171  
Fax: (44)-1793-616652

*All of the above information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics makes no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. Tyco Electronics only obligations are those in the Standard Terms and Conditions of Sale for this product and in no case will Tyco Electronics be liable for any incidental, indirect or consequential damages arising from the sale, resale, use or misuse of the product. Tyco Electronics Specifications are subject to change without notice. In addition Tyco Electronics reserves the right to make changes in materials or processing, without notification to the Buyer, which do not affect compliance with any applicable specification.*

RI0051.1299